



## PROPERTIES

TROWEL/GLOVE	COLOR	BRUSH/SPRAY
35-00	White	45-00
35-01	Aluminum Gray	45-01
Other colors available on special order		

**AVERAGE WEIGHT/U.S. GALLON (FSTM 3):**  
11.2 lbs (1.34 kg/l)

**AVERAGE NON-VOLATILE (FSTM 9A):**  
63-65% by volume (73-75% by weight)

**COVERAGE RANGE:**  
(Subject to the nature of material coated). Wet coverages shown below are for smooth non-porous surfaces. Porous or rough surfaces will require higher gallonage to attain required dry thickness.

**DRY THICKNESS:** 0.062 inch (1.6 mm)

**EQUIVALENT WET COVERAGE:** 0.096 inch (2.4 mm)  
6 gal/ 100 sq. ft. (2.4 l/m<sup>2</sup>)

**DRYING TIME (ASTM D 1640):**  
Set to Touch: 3 hours  
Dry Through: 16 hours

**SERVICE TEMPERATURE LIMITS (FSTM 70):**  
(Temperature at coated surface)  
-20°F to 200°F (-29°C to 93°C)

**WATER VAPOR PERMEANCE (ASTM F 1249):**  
3.0 perms (2.0 metric perms) at 1/16 inch (1.6 mm) dry film thickness; decreasing on aging to 1.0 perm (0.7 metric perm)

**WET FLAMMABILITY (ASTM D 3278):**  
No flash to boiling, 205°F (96°C)

**SURFACE BURNING CHARACTERISTICS (ASTM E 84):**  
Flame Spread: 20  
Smoke Developed: 25-50  
Tested at coverage rate of 16.7 sq. ft. per gallon (6 gal/100 sq. ft., 2.4 l/m<sup>2</sup>).  
Applied to 1/4 inch (6.4 mm) inorganic reinforced cement board. The flame spread may vary at different product thicknesses and/or when applied over other surfaces.

™ Trademark of Specialty Construction Brands, Inc.

## FOSTER® SEALFAS G-P-M® MASTIC



**Foster® Sealfas G-P-M® Mastic** is a high solids waterbase general purpose mastic having excellent trowel and spray properties. G-P-M is used for the protection of thermal insulation and hard, dry cement coats, both indoors and outdoors.

**Sealfas G-P-M Mastic** is fire-resistive and features ease of application, non-flammability, non-toxicity, mild odor, insulation compatibility, good package stability, plus excellent outdoor durability.

**Sealfas G-P-M Mastic** meets NFPA 90A & 90B 25/50 requirements.

**Sealfas G-P-M Mastic** is produced under the classification and follow-up service of Underwriter's Laboratories, Inc.

**Sealfas G-P-M Mastics** 35-00 and 45-00 conform with current requirements regarding use in meat and poultry processing areas under federal inspection. Letter of certification is available upon request.

**Nuclear Grade Sealfas G-P-M** 35-00Q and 45-00Q can be supplied to meet the stress corrosion and chemical analysis requirements of MIL-I-24244C or nuclear regulatory guide 1.36 on special order.

**Sealfas G-P-M Mastic** meets requirements for LEED IEQ 4.2 Low-Emitting Materials, Paints and Coatings. VOC (35-00): 37 g/l, less water and exempt solvents. VOC (45-00): 36 g/l, less water and exempt solvents.

**Sealfas G-P-M Mastic** contains no asbestos, lead, mercury, or mercury compounds.

### LIMITATIONS

Store and apply between 40°F (4°C) and 100°F (38°C), protect from freezing until dry.

To resist rain washoff, allow at least 16 hours drying time above 40° F (4°C), with a relative humidity of 50%. Higher humidity at lower temperatures may retard drying.

Always test paper facings for acceptable adhesion before using. Select WEATHERITE™ Mastics for use over foil facings.

Outdoor horizontal surfaces must always drain completely. A pitch of at least 1/2 inch per foot (4 cm/m) is recommended.

Always select 35-00 or 45-00 white for use over polystyrene insulation installed outdoors.

Visit us on the web at [www.fosterproducts.com](http://www.fosterproducts.com)

0809

**Specialty Construction Brands, Inc.**  
an H.B. Fuller Company

1105 South Frontenac Street ○ Aurora, IL 60504 ○ 800-231-9541 ○ fax 800-942-6856

# APPLICATION GUIDE FOR FOSTER® SEALFAS G-P-M® MASTIC 35-00/45-00™

## MATERIAL PREPARATION

DO NOT THIN. Foster® Sealfas G-P-M® Mastic will appear to be thick, but this is a "false" consistency which "breaks down" readily on application. Stirring is not necessary. Apply only to clean, dry, oil-free surfaces. Keep container closed when not in use.

## APPLICATION - HEAVY DUTY, HOT AND DUAL TEMPERATURE SERVICE

(Follow flashing recommendations when installed outdoors.)

For best results, prime hygroscopic alkaline cements with Foster® 40-22™ Masonry Sealer and Primer or Foster® 40-26™ Waterbase Primer. Both the cement and the primer must be completely dry before the Foster Sealfas G-P-M Mastic is applied.

**MAST-A-FAB® REINFORCEMENT** Apply a tack coat of Foster Sealfas G-P-M Mastic at a thickness of 1/32 inch (0.8 mm). This is equivalent to 2 gal./100 sq. ft. (0.8 l/m<sup>2</sup>).

Embed Foster Mast-A-Fab white membrane into wet tack coat. Smooth membrane to avoid wrinkles and overlap all seams at least 2 inches (5 cm). Apply a finish coat of Foster Sealfas G-P-M Mastic at a minimum thickness of 1/16 inch (1.6 mm). This is equivalent to 4 gal./100 sq. ft. (1.6 l/m<sup>2</sup>). This finish coat shall be applied no later than 1/2 hour after the tack coat and shall completely cover the membrane.

This application shall provide a minimum dry film thickness of 62 mils (1.6 mm).

## HEAVY DUTY APPLICATIONS - UP TO 50% GREATER TENSILE STRENGTH

Apply as above, substituting Childers™ Chil-Glas® #5 as the reinforcing membrane. Note that the membrane weave pattern will show through the dried mastic.

## TROWEL

Use clean steel trowel. Apply in full thickness promptly. Avoid excessive troweling.

## Brush


Use a good brush (suitable for water based paints), making strokes as long as possible over the surface. Apply with full brush and spread out evenly. Do not overwork. Multiple coats will be needed to achieve the minimum dry film thickness.

## SPRAY

Foster Sealfas G-P-M Mastic (45-00 series) may be spray applied with heavy duty pneumatic airless equipment. For spray equipment information, please consult Airless Spray Recommendations or contact your spray equipment supplier. Average Viscosity Range: 60,000 - 100,000 cps. Corrosion resistant pumps and fittings are suggested.

## CLEAN-UP

Use fresh water to clean equipment before product dries. Dry product may be removed with hot soapy water or solvents such as chlorinated solvent (non-flammable) or xylol (flammable).

	GENERAL PURPOSE COATING	
	SURFACE BURNING CHARACTERISTICS	
Applied to 1/4" Inorganic Reinforced Cement Board		
Flame Spread:		20
Smoke Developed:		20-25
Rate per Coat (Sq.ft/gallon):		16 to 17
Number of Coats		1
Flash point of liquid coating (closed cup): no flash		
282U		



## CUSTOMER SERVICE: 800-231-9541

IMPORTANT: Specialty Construction Brands, Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is six months from date of shipment to the original purchaser.

**For professional use only. Keep out of reach of children.**

**Consult Material Safety Data Sheet and container label for further information.**