# **PVC Fitting Covers and Jacketing**



# Ceel-Co® PVC

Installation Accessories

#### **DESCRIPTION**

Ceel-Co installation accessories offer outstanding compatibility and performance in the systems for which they are designed. When used in conjunction with the various Ceel-Co products, they complete a systems package that features ease of installation, uniform appearance and optimum long-term insulation and protection.

A complete Ceel-Co system, using components and accessories that are fully integrated, will give you an easy-to-install, professional job that offers peak performance in a neat, uniform installation.

# **CEEL-TITE® SOLVENT WELDING SYSTEM ADHESIVE**

Ceel-Tite solvent welding system adhesive is applied with a standard applicator gun and forms a permanent chemical bond between the PVC members. It takes an initial set in 10 minutes with complete adhesive curing in 8 to 10 hours. Ceel-Tite adhesive contains approximately 21% solids. If applied at a rate of 5 mils (0.005 inches), the coverage rate would be 320 square feet per gallon, resulting in a dried film approximately one mil thick. Ceel-Tite adhesive can be used on 20 and 30 mil (0.5mm and 0.8 mm) jacketing and most Ceel-Co 550/300 PVC insulated fitting covers where a totally sealed system is required, such as in the USDA market. Ceel-Tite adhesive is available in one quart (0.95 liter) and one gallon (3.8 liter) containers.

**Note:** It is recommended that Ceel-Tite adhesive be applied at temperatures above 40°F (4°C). Recommended use within 9–12 months of date code.

#### **CEEL-TITE ADHESIVE APPLICATOR**

Pump-type gun for application of Ceel-Tite adhesive. Holds 6 ounces (177 ml).

# CEEL-TITE® THINNER

Ceel-Tite Thinner is used primarily for clean-up or removal of Ceel-Tite Adhesive from applicator guns and equipment. Available in single gallon (3.8 liter) containers or packed six quarts (0.95 liters/container) per case, it should be used sparingly to thin adhesive if necessary.

#### **PVC Z-TAPE**

Z-Tape was developed to provide excellent adhesion, even when applied during cold or humid weather. It is flexible polyvinyl chloride film, coated with a specially formulated adhesive. Z-Tape is available in thicknesses of 5 mils (0.13 mm) and 10 mils (0.25 mm) and can be applied indoors and outdoors\* at temperatures as low as 40°F (4°C) to achieve a strong, permanent bond. It has an effective installed temperature range of 0°F to 150°F (-18°C to 66°C).

Z-Tape has excellent resistance to chemicals, acids, alkali, oils, greases, bacteria, and fungus. It can bridge gaps and cover almost any contour or shape for a complete seal.

\*Z-Tape II is recommended for indoor use only.



#### **SPECIFICATION DATA**

Property	Z-Tape II*	Z-Tape*
Gauge, mils (mm)	5 ±0.5 (0.13 ± 0.013)	10 ±1 (0.25 ±0.025)
Available color	White	White
Upper temperature limit	150°F (66°C), constant	150°F (66°C), constant
Lower temperature limit	0°F (-18°C), constant	0°F (-18°C), constant
Surface Burning	Flame spread: 5	Flame spread: 10
Characteristics per ASTM E84	Smoke developed: 0	Smoke developed: 0
Adhesion to backing, oz./in. (kg/mm)	14 (0.02)	30 (0.033)
Tensile strength lbs./in. width (kN/m)	15 (2.6)	27 (4.7)
Elongation (%)	150	200
Finish	Smooth	Smooth
Dimensions	Available in 1," 1½" and 2" (25 mm, 38 mm and 51 mm) widths	Available in 1," 1½" and 2" (25 mm, 38 mm and 51 mm) widths
	Standard lengths: 1088 (33 m)	Standard lengths: 1008 (31 m)
Conforms to	1" (25 mm) size 12 per ctn.	1" (25 mm) size 12 per ctn.
MIL-I-7798-C	1½" (38 mm) size 8 per ctn.	1½" (38 mm) size 8 per ctn.
standard packaging	2" (51 mm) size 6 per ctn.	2" (51 mm) size 6 per ctn.

<sup>\*</sup>Tests are conducted in accordance with ASTM D1000. Values indicated are typical.

#### WHITE, STAINLESS STEEL THUMB TACKS

Annular serrated stainless steel thumb tacks, 500 to a box, help speed the installation of Ceel-Co PVC insulated fitting covers on hot work where a vapor retarder is not required.

### **INSTALLATION**

For complete installation instructions, please see CI-35 brochure.

PVC Z-TAPE WIDTH RECOMMENDED AND APPROXIMATE NUMBER OF COVERS SEALED PER ROLL OF TAPE (INCLUDES 2" [51 MM] TAPE OVERLAP)

Tape width to use		Ceel-co cover	No. of cove per roll	No. of covers per roll	
in	mm	size	90s & 45's	Tees	
1 25	1	84	56		
		2	80	53	
		3	73	49	
		4	67	44	
		5	61	41	
		6	56	38	
		7	53	35	
	8	48	32		
1½ 38	9	44	29		
	10	40	27		
	11	36	24		
		12	32	22	
	13	30	20		
		14	28	19	
		15	26	17	
		16	24	16	
		17	23	15	
		18	20	14	
		19	18	12	
		20	17	11	
2	51	21	15	10	
		22	14	9	
	23	13	9		
	24	12	8		
	25	11	8		
	26	11	7		
		27	10	7	
	28	10	6		
	29	9	6		
		30	9	_	
	32	8	_		

Long radius 90° (1.6 Rad.) sizes		No. of covers per roll*	Long radius 90° (1.6 Rad.) sizes		No. of covers per roll*
in	mm		in	mm	
2 x 1	51 x 25	36	14 x1	356 x 25	11
25/8 x 11/2	67 x 38	30	14 x 1½	356 x 38	11
3 x ½	76 x 13	36	14 x 2	356 x 51	10
3 x 1	76 x 25	30	14 x 3	356 x 76	9
4 x ½	102 x 13	30	16 x 1	406 x 25	10
4 x 1	102 x 25	26	16 x 1½	406 x 38	10
5 x ½	127 x 13	26	16 x 2	406 x 51	9
5 x 1	127 x 25	23	16 x 3	406 x 76	8
6 x ½	152 x 13	23	18 x 1	457x 25	9
6 x 1	152 x 25	20	18 x 1½	457 x 38	9
6 x 1½	152 x 38	18	18 x 2	457 x 51	8
8 x ½	203 x 13	18	18 x 3	457 x 76	8
8 x 1	203 x 25	17	20 x 1	508 x 25	8
8 x 1½	203 x 38	15	20 x 1½	508 x 38	8
8 x 2	203 x 51	14	20 x 2	508 x 51	8
10 x 1	254 x 25	14	20 x 3	508 x 76	7
10 x 1½	254 x 38	13	24 x 1	610 x 25	7
10 x 2	254 x 51	12	24 x 2	610 x 51	6
12 x 1	305 x 25	12	24 x 3	610 x 76	6
12 x 1½	305 x 38	11			
12 x 2	305 x 51	11			
12 x 3	305 x 76	10			

<sup>\*</sup>Use 29 (51 mm) tape only.



717 17th St.
Denver, C0 80202
(800) 654-3103
specJM.com
CI-220 09/10 (Replaces 05/05)

# North American Sales Offices, Insulation Systems

# **Eastern Region**

P.O. Box 158 Defiance, OH 43512 (800) 334-2399 Fax: (419) 784-7866

## Western Region and Canada P.O. Box 5108 Denver CO 80217

Denver, CO 80217 (800) 368-4431 Fax: (303) 978-4661 The physical and chemical properties of Ceel-Co® PVC Installation Accessories listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you to assure current information. All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, including Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions, Limited Warranty and Limitation of Remedy and information on other Johns Manville thermal insulation and systems, call (800) 654-3103.