

# PC® 88 adhesive PRODUCT DATA SHEET

IMPORTANT: MATERIAL SAFETY DATA SHEETS ARE AVAILABLE AND SHOULD BE READ BEFORE USING THIS PRODUCT.

## DESCRIPTION:

PC® 88 is a two part adhesive for bonding FOAMGLAS® insulation to itself or to other porous or nonporous substrates. Air curing is not required. It has excellent wetting characteristics and cures to form a flexible bond that absorbs mechanical and thermal shock..

## \*TYPICAL PROPERTIES:

| PROPERTY  |                         | ASTM TEST |
|---|-------------------------|-----------|
| Color:  | Black                   |           |
| Density: kg/l, (lbs/gal)                          | 1.01-1.15<br>(8.4-9.6)  |           |
| Solids Content( % by wt.)                         | 92-96                   |           |
| Coverage m <sup>2</sup> /l (ft <sup>2</sup> /gal) | 0.5 (20)                |           |
| Flash Point, PMCC °C (°F)                         | >65.5 (150)             |           |
| Flame Resistance( cured)                          | combustible             |           |
| Application Temperature, Material °C, (°F):       | 20-35 (70-90)           |           |
| Surface min °C, (°F) :                            | 5 (40)                  |           |
| Service Temperature °C, (°F)                      | -56 to 82, (-70 to 180) |           |
| Working Time, min @ 25°C (77°F) minutes:          | 90                      |           |
| Water Vapor Permeability perm-cm, (perm-in)       | 0.008, (0.005)          | E96       |

\* Properties subject to change. Consult Pittsburgh Corning Corporation.

## SURFACE PREPARATION:

Surfaces must be free of moisture, loose scale and rust, dust, oil and grease. Asphaltic primers, coal tars, silicones, alkyd or other solvent sensitive or thermoplastic primers or coatings should not be used. Some acceptable primers are zinc rich, polyester and epoxy. If in doubt, always check surface for adhesion before starting work with a test block. Apply a small block and let cure for a minimum of 24 hours. Block should break before adhesive peels from surface. A one quart kit is available on request for test purposes.

## MATERIAL PREPARATION:

THIS IS A TWO COMPONENT MATERIAL THAT MUST BE MECHANICALLY MIXED PRIOR TO USE. BE SURE YOU HAVE READ AND UNDERSTAND ALL INSTRUCTIONS, CAUTIONS, AND MATERIAL SAFETY DATA SHEETS CONTENTS BEFORE USING.

To avoid waste and obtain desirable properties, certain procedures must be followed. Temperature of adhesive, substrate and the ambient temperature will affect working time and cure. Higher temperatures reduce working time, viscosity and cure. Lower temperatures increase viscosity and lengthen the working time and cure. Store adhesive out of direct sunlight and at temperatures as close to 25°C (77°F) as possible and for at least 2 hours before use.

Lay out work before mixing. Make sure equal containers of Component 1 [19 liter (5 gal) pail] and Component 2 [0.4 liter (12 oz.) can] have been received and are on the job site.

Mix Component 1 two to three minutes before adding Component 2. A 19 mm (3/4 in.) heavy duty drill and good mixing paddle or PC mixer is required. When work is ready, add Component 2 to Component 1 and mix for approximately 5 minutes. Move mixer around inside the pail. Incomplete mixing can lead to incomplete cure and residual odors.

Blocks of insulation should be checked for fit to the substrate surface before adhesive is mixed or work started. Blocks must be reshaped or cut smaller if they do not fit, especially on overhead work.

## FIELD APPLICATION:

Adhesive may be applied to either or both surfaces. Application to the rougher surface (i.e., FOAMGLAS® insulation) generally gives the best results. A notched trowel having a D notch of 2.4 mm (3/32 in.) deep, 2.4 mm (3/32 in.) wide with a 3.2 mm (1/8 in.) flat surface between notches is standard (Red Devil 2001/A-7 or "A" notch from others). Adhesive must be spread and blocks applied within the working time and before adhesive sets. Adhesive that has set can not be recovered. On curved or overhead surfaces, temporary support and/or the HOLD CATALYST system may be needed.

On low temperature equipment, all joints must be completely sealed with adhesive and all voids must be completely filled as possible. Joints should be sealed and any exuded adhesive wiped off before

# PC® 88 adhesive PRODUCT DATA SHEET

adhesive sets. Adhesive on the face of the block may cause coating adhesion problems. If insulation is to be coated, blocks should be rubbed down to provide a uniform surface.

Trowels should be cleaned frequently and examined for wear. Clogged or worn trowels can cause either too little or too much adhesive being used.

Adhesive that has set can not be recovered. Additional coats of adhesive must be applied within 8 hours to assure bonding to the previous coat. If adhesive has cured more than 8 hours, rub briskly with a commercial gloss remover or abrade before recoating.

#### CLEAN-UP AND DISPOSAL:

Mineral spirits or kerosene.

See Material Safety Data Sheets for proper disposal.

#### LIMITATIONS:

Do Not use as exterior coating exposed to sunlight or to be re coated. Keep closed when not in use.

Do Not use where odor could affect food.

#### PACKAGING:\*

15 l ( 4 gal.) kit:

Component 1: 15 l (4 gal.) in a 19 l (5 gal.) pail

Component 2: 296 ml (10 oz.) in a 355 ml (12 oz) can

7.6 l (2 gal.) kit:

Component 1: 7.6 l (2gal.) in a 11.4 l ( 3 gal.) pail

Component 2: 148 ml (5 oz.) in a 355 ml (12 oz) can

\*For domestic ground shipments, Component 2 is shipped inside the Component 1 container. For International or Air shipments, Component 1 and Component 2 are shipped separately.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning Corporation has no control over installation workmanship, accessory materials or conditions of application, **NO EXPRESS OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE** as to the performance of an *installation* containing Pittsburgh Corning products. In no event shall Pittsburgh Corning be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning Corporation provides written warranties for many of its products, and such warranties take precedence over the statements contained here

PC® and FOAMGLAS® is a federally registered trademark owned by Pittsburgh Corning Corporation

Pittsburgh Corning Corporation  
800 Presque Isle Drive Pittsburgh, PA 15239-2799  
USA

Toll Free: 800-545-5001

Phone: (724)327-6100

Fax: (724)387-3806

<http://www.foamglas.com/>

Pittsburgh Corning Europe S.A./ N.V.  
(EMEA Headquarters)

Albertkade 1

3980 Tessenderlo

Belgium

Phone: +32-13-611-415

Fax: +32-13-351-567