



(800)874-1748  
(440)439-1300  
Fax: (440)439-7236

7200 Northfield Road · Cleveland, Ohio 44146

www.gltproducts.com

---

## REWETTABLE FIBERGLASS CLOTH – STYLE 1989

### DATA SHEET

---

**DESCRIPTION** – Style 1989 Rewettable Fiberglass Cloth is a 100% asbestos free lagging fabric. Style 1989 Rewettable Fiberglass Cloth is made from texturized yarns for maximum coverage and ease in application, and is combined with a completely inorganic fire retardant adhesive which is impregnated throughout the fabric. This lagging fabric is ideal for use in repairing or covering insulation that has been damaged or has become friable on piping, tanks, vessels, boilers and breechings. Style 1989 Rewettable Fiberglass Cloth will retain a service temperature of 1000°F (538°C).

**APPLICATION DATA:** After immersing in water, remove excess water (do not wring out). Apply directly to damaged insulation and smooth out wrinkles. After allowing approximately 4 to 8 hours to dry, coat with an approved paint, mastic or bridging compound.

#### PHYSICAL SPECIFICATIONS:

Thread Count	20 x 14 (+/-2)
Weight (oz./sq.yd.)	14.5 (+/-10%)
Thickness	.04 inches (+/- 10%)
Tensile (warp/fill)	100/40
Weave	2 end plain
Shelf Life	1 year
Upper Temperature Limit	1,000°F (538°C)
Available Sizes	40" x 150' 60" x 150'